

PSX® 700 A CLEAR COAT

DESCRIPTION

Two-component, engineered polysiloxane clearcoat

PRINCIPAL CHARACTERISTICS

- Universal clear finish compatible with primed steel, clean metals and concrete
- High durability in challenging environments
- Resists dirt pickup, easily cleaned
- Resists graffiti
- High solids, low VOC
- Isocyanate free

COLOR AND GLOSS LEVEL

- Clear
- Gloss

BASIC DATA AT 20°C (68°F)

Data for product	
Number of components	Two
Mass density	1.1 kg/l (9.2 lb/US gal)
Volume solids	78 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 200.0 g/kg max. 222.0 g/l (approx. 1.9 lb/gal) (aluminum)
Recommended dry film thickness	20 - 25 µm (0.8 - 1.0 mils) per coat
Theoretical spreading rate	39.0 m ² /l for 20 µm (1564 ft ² /US gal for 0.8 mils) 31.2 m ² /l for 25 µm (1251 ft ² /US gal for 1.0 mils)
Dry to handle	5 hours
Overcoating Interval	4 hours Maximum: 30 days
Full cure after	7 days
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



PSX® 700 A CLEAR COAT

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate condition

- Existing sound coating systems; sufficiently roughened, dry and cleaned
 - Surface must be dry and free from any contamination
-

Concrete

- Dried for at least 28 days in good ventilation conditions
 - Moisture content should not exceed 4.5%
 - Concrete must be sound, dry, free from laitance and any contamination
 - Rough surface; eventually abraded by power tool or diamond abrading tool
-

Non-ferrous metals and stainless steel

- Surface must be free from grease, salts and any contamination
 - Surface should be sufficiently roughened (e.g. sandpapering, sweep blasting)
-

Substrate temperature and application conditions

- Surface temperature during application should be between 5°C (41°F) and 50°C (122°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Ambient temperature during application and curing should be between 5°C (41°F) and 50°C (122°F)
 - Relative humidity during application and curing should be between 50% and 85%
-

SYSTEM SPECIFICATION

- One or two coats of 20 - 25 µm (0.8 - 1.0 mils)
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 83:17 (5:1)

- The temperature of the mixed base and hardener should be above 10°C (50°F), otherwise extra thinner may be required to obtain application viscosity
 - The paint should be stirred well before use, preferably by means of a mechanical mixer, to ensure homogeneity
 - Add hardener to base and continue stirring until homogeneous
 - If required, thinner should be added after mixing the components
 - Adding too much thinner results in reduced sag resistance and slower cure
-

Induction time

None

Pot life

4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life



PSX® 700 A CLEAR COAT

Air spray

Recommended thinner

THINNER 60-12

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.0 - 1.5 mm (approx. 0.040 - 0.060 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

Airless spray

Recommended thinner

THINNER 60-12

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.38 - 0.43 mm (0.015 - 0.017 in)

Nozzle pressure

15.0 - 18.0 MPa (approx. 150 - 180 bar; 2176 - 2611 p.s.i.)

Brush/roller

Recommended thinner

THINNER 60-12

Volume of thinner

0 - 5%

Cleaning solvent

THINNER 90-53 or THINNER 90-58

PSX® 700 A CLEAR COAT

ADDITIONAL DATA

Overcoating interval for DFT up to 25 µm (1.0 mils)					
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	12 hours	8 hours	4 hours	2 hours
	Maximum	30 days	30 days	30 days	30 days

Note: Surface should be dry and free from any contamination before recoating

Curing time for DFT up to 25 µm (1.0 mils)		
Substrate temperature	Dry to handle	Full cure
5°C (41°F)	16 hours	16 days
10°C (50°F)	9 hours	10 days
20°C (68°F)	5 hours	7 days
30°C (86°F)	3 hours	5 days

Notes:

- Adequate ventilation must be maintained during application and curing
- Relative humidity lower than 40% will extend the drying times

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	3 hours
40°C (104°F)	2 hours

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



PSX® 700 A CLEAR COAT

REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

