

PITT-CHAR® XP

DESCRIPTION

Two-component, 100% solids, flexible, epoxy intumescent fire protective coating for use in industries such as oil & gas, chemicals, energy, transportation and defence that potentially involve major accident hazards including explosions, hydrocarbon jet and pool fires and cryogenic spills

PRINCIPAL CHARACTERISTICS

- Provide passive fire protection to structures, divisions (decks, bulkheads and firewalls), process vessels, pipework and equipment which are safety critical. Ensure structural stability, integrity, meeting insulation requirements
- Highly durable, epoxy intumescent coating that offers excellent corrosion protection
- Resistant to industrial environments including splash and spillage of chemicals
- Suitable for use in offshore and onshore environment with ISO 12944-2 corrosivity categories of C5-I and C5-M
- Suitable for protecting substrates including aluminium, carbon steel, galvanized steel, stainless/duplex steels, fibre reinforced polymers and concrete
- Suitable for use as protection against cryogenic spills to prevent steel embrittlement
- Resistant to the damage from vibration, abrasion, and impact from deflection of structures during fabrication, transportation and extreme loading conditions
- Withstands vapour cloud explosion events including over-pressure, drag and secondary projectile impact forces
- Unique, patented elastomeric formulation provides excellent flexibility and ductility
- Can be applied by spray, nozzle or trowel. Suitable for moulding or extruding into finished goods
- Independently tested in accordance with international recognized standards including ASTM E-84, BS 476, ISO 834, ISO 22899, ISO 20340, NFPA 290, NORSOK M501 Edition 6, UL 1709, UL 263, IMO FTP Code, GASAFE, China GB 14907, and Russian GOST
- Type approval and certification by industry leading bodies including ABS, BV, DNV, LR, KMERI, China 3C, Russian Maritime and UL
- Operating Temperature Limits: -40°C (-40°F) to +80°C (176 °F) continuous; for short term/infrequent excursions beyond these limits please contact PPG for advice

COLOR AND GLOSS LEVEL

- Gray (not available in tints)
- Matt
- Available topcoats in wide range of colors

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.0 g/cm ³ (62.4 lb/ft ³) (ISO 1183-1:2012 Method A - Spray Applied)
Volume solids	100%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 0.0 g/kg max. 0.0 g/l (approx. 0.0 lb/US gal)



PITT-CHAR® XP

Data for mixed product

Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry
-------------------	--

Notes:

- Material should be stored in dry conditions, out of direct sunlight and at temperatures above 0°C (32°F) and below 35°C (95°F)
- The applied density is dependent upon many variables such as temperature, test method, application method and equipment
- Required dry film thickness must be in accordance with requirements of fire approval certification
- Apply appropriate loss/wastage factor

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Substrate must be sound, dry and free from any contamination and surface prepared in accordance with PITT-CHAR® XP APPLICATION GUIDELINES
- Primer system should be within specified thickness, fully cured, and within over-coating interval guidelines for the system used
- Only primers qualified for use with Pitt-CHAR XP shall be used, please refer to PPG's INFORMATION SHEET 1204
- For non-PPG primers or topcoats, please contact your PPG representative
- Where mesh reinforcement of PITT-CHAR® XP is necessary, this should be carried out in accordance with the PITT-CHAR® XP APPLICATION GUIDELINES

Substrate temperature and application conditions

- Ambient temperature below 10°C (50°F) is acceptable; however curing to hardness takes longer, and it will cease curing below 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Relative humidity during application and curing should not exceed 85%

Note: Curing will effectively cease below 5°C (41°F), but once temperature rises again, it will continue to cure

INSTRUCTIONS FOR USE

- Application should be strictly in accordance with PITT-CHAR® XP APPLICATION GUIDELINES

Mixing ratio

- By volume: base to hardener 2.33 : 1
- By weight: base to hardener 3.05 : 1

Note: Tolerance +/- 10%. When applying by single feed spray pump or trowel application, it is recommended that full kits are mixed

PITT-CHAR® XP

Airless Spray – Heated Plural Component (Preferred)

- Hoses should normally be kept as short as possible

Recommended thinner

No thinner should be added

Nozzle angle

40° – 60°

Nozzle orifice

Approx. 0.79 – 1.09 mm (0.031 – 0.043 in)

Nozzle pressure

24.0 - 31.0 MPa (approx. 240 - 310 bar; 3481 - 4496 p.s.i.)

Notes:

- See PITT-CHAR® XP APPLICATION GUIDELINES for full details
- Base and hardener need to be pre-heated to a minimum of 55 - 60°C (131 - 140°F) while circulating through the unit
- Suitable insulated and/or heated hoses should be used
- After airless application, please make surface smooth with roller using recommended thinners

Airless Spray – Single Feed Pump

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 7%, but the quantity shall never exceed 10%

Nozzle angle

40° – 60°

Nozzle orifice

Approx. 0.69 – 0.89 mm (0.027 – 0.035 in)

Nozzle pressure

35.0 MPa (approx. 350 bar; 5077 p.s.i.)

Notes:

- The addition of thinner will affect sag resistance and overcoating intervals
- Contact PPG representatives for alternative thinner
- Material (mixed) temperature needs to be between 23°C (73°F) and 35°C (95°F)
- The maximum length of the hoses should not exceed 30 m (98.4 ft)
- Use of spray equipment with a ratio of 74:1 is recommended
- After airless application, please make surface smooth with roller using recommended thinners

PITT-CHAR® XP

Trowel

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 2%

Notes:

- Recommend that only full kits are mixed and applied (avoid part kits to ensure correct mix ratio)
- Recommended for small areas and touch-up only
- Contact PPG representatives for alternative thinner

Cleaning solvent

THINNER 91-92 or THINNER 90-53

ADDITIONAL DATA

Overcoating interval for solvent-free coatings

Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself, tiecoat, polyurethane or epoxy top coat	Minimum	30 hours	20 hours	15 hours	12 hours	8 hours	4 hours
	Maximum	3 months	3 months	3 months	2 months	2 months	1 month

Notes:

- Surface should be dry and free from any contamination
- If solvent thinners have been added, minimum over-coating intervals should be extended to prevent solvent entrapment
- See PITT-CHAR® XP APPLICATION GUIDELINES for full details

Curing time for solvent-free application

Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	26 hours	3.5 days	1.5 months
10°C (50°F)	22 hours	52 hours	30 days
20°C (68°F)	9 hours	18 hours	15 days
30°C (86°F)	7 hours	10 hours	10 days
40°C (104°F)	3 hours	7 hours	7 days

Notes:

- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- Curing times may vary depending on substrate, ambient and material temperature
- Drying times have to be doubled from dry to handle time for walk-on
- See PITT-CHAR® XP APPLICATION GUIDELINES for full details



PITT-CHAR® XP

Pot life (at application viscosity)	
Mixed product temperature	Pot life
25°C (77°F)	45 minutes
35°C (95°F)	20 minutes

Note: Pot life is dependent on many variables including material temperature, substrate temperature, mixing time, addition of solvent, etc. Figures provided are for guidance only

Product Qualifications

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes

REFERENCES

• PITT-CHAR® XP APPLICATION GUIDELINES	INFORMATION SHEET	1202
• PITT-CHAR® XP QUALIFIED PRIMER LIST	INFORMATION SHEET	1204
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650
• CONVERSION TABLES	INFORMATION SHEET	1410
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgmcc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.