

PPG PITT-CHAR® CF SCRIM MESH

DESCRIPTION

Carbon fiber mesh for use as a reinforcement scrim in the PPG PITT-CHAR NX and PPG PITT-CHAR XP epoxy intumescent passive fire protection systems

PRINCIPAL CHARACTERISTICS

- Appearance; black woven mesh (8 x 4 Leno weave)
- High temperature resistance, suitable for hydrocarbon pool and jet-fire protection
- Simple to cut and apply into wet film of coating; no welded pins or mechanical fixings required
- High purity carbon fiber mesh; carbon content is greater than 99%
- Excellent resistance to chemicals and solvents
- To be installed strictly in accordance with PPG PITT-CHAR Application Guidelines and fire certification requirements

BASIC DATA

Data for product	
Weight	Minimum weight 54 g/m ² (1.6 oz/sq. yards)
Nominal roll area	125 m ² (1350 sq. ft.)
Roll size	Roll width: 914 ± 50 mm (36 ± 2 in.); Roll length: 137.2 ± 4.6 m (150 ± 5 yards)
Mesh size	6.35 x 6.35 mm (¼ x ¼")
Shelf life	Extended; should be stored in original packaging in clean and dry conditions

Note: Mesh is wound on a 75 mm (3 in) diameter cardboard core, sealed in a polyethylene bag and placed in a 305 x 305 x 1143 mm (12 in x 12 in x 45 in) cardboard box

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

